

ART 34 AMDT


10/522852
PCT, 2002/002251
IPEA/KR 01.10.2004

DT12 Rec'd PCT/PTO 28 JAN 2005


Claims

1. (amended) A coating composition for a plastic photochromic lens, comprising 1.5 to 5 wt% spiropyran compound defined by Formula I and spirooxazine compound defined by Formula II; 60 to 65 wt% toluene; and an acryl
5 based binder to make 100 wt% of the coating composition.

Formula I



Formula II



10

(wherein,

R is alkyl with 1 to 30 carbon atoms;

R1 is alkyl, alkenyl, or alkoxy with 1 to 10 carbon atoms, or substituted or non-substituted phenyl;

15 R2 to R5 are independently hydrogen atom, halogen, cyano, nitro, or alkyl or alkoxy with 1 to 6 carbon atoms; and

X is hydroxy, glycidoxy, amine, or dichlorotrioxazinoxy)

2. (unchanged) A plastic photochromic lens coated with the coating composition according to claim 1.

3. (unchanged) A method of producing a plastic photochromic lens, comprising:

- 5 coating a surface of a plastic lens with the coating composition according to claim 1; and
 heat-curing the resulting structure.

4. (unchanged) The method according to claim 3, wherein the heat-curing is performed at the temperature of 30 to 80°C.